AAG NITRILE P459

technical data sheet



10 24/01 2023

General:

NBR-SBR, black, high-grade Sulphur crosslinked For medium mechanical demands

Good oil resistant fuel resistant (alcohol-free fuels)

Wrapping: stretched foil, labelled standard finishing in separation foil

*SVHC-free

Working temperature range

Air (-10)°C +70°C	+90°C

Compression set DIN ISO 815

Duration	Temperature	CS
22h	+70°C	40%

Ageing ISO 188

Conditions	Hardness	Strength	Elongation
70h / 70°C	7 Shore A	10%	20%

Swelling ISO 1817

Medium	Conditions	Hardness	Volume
IRM 903	70h / 100°C	10 Shore A	15 %
Fuel B	70h / 23°C		20 %

ROTACURED SHEETS Length mm product number mm 401140100 1,0 1 400 20 000 401140150 1,5 1.400 2.0 401140200 1.400 20.000 401140300 3,0 1.400 10.000 401140400 4.0 1,400 10,000 401140500 5,0 1.400 10.000 401140600 6.0 1.400 10.000 401140800 8,0 1.400 5.000 1.400 401140000 10.0 5.000

Properties:

 Hardness [Shore A]:
 ISO 7619-1
 65±5

 Density [g/cm³]:
 ISO 1183-1
 ~1,45

 Tensile Strength [N/mm²]:
 ISO 37 type 2
 7

 Elongation at Break [%]:
 ISO 37 type 2
 250

 ACN content:
 33 %

correspond to WDK-guideline 2201 : 2020-10 "Quality characteristics of Elastomer sheets- and plates"

Stabilities:

Ozone resistance: non resistant
Weather resistance: non resistant
Oil resistance: good resistant
Fuel resistance: resistant

only alcohol-free fuels!

Acid resistance: moderately resistant Strong bases: moderately resistant Abrasion resistance: non suitable

PRESS-CURED SHEETS product number	Thickness mm	Width mm	Length mm
421340120	12,0	1.400	5.000
421340150	15,0	1.400	5.000
421340200	20,0	1.400	5.000
421340250	25,0	1.400	5.000
421340300	30,0	1.400	5.000
421340400	40,0	1.400	5.000
421340500	50,0	1.400	5.000

PAH disclaimer:

Referring to an international proficiency test and information received from the testing laboratories about accuracy of test results we may inform you, that test results for the same specimen from different laboratories may not correlate:

Our test results are provided on an as-is basis and to the best of our knowledge, without any legally binding commitment. Our tests do not release you from own tests as to the respective application envisaged.

Please note:

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualitied engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course warrant the quality of our products according to our General Sales Conditions, available on our website or on request

Results of the 10 PAH with individual limits of < 1 mg/kg in the measurement range around the limit are only accurate to approx. ± 70%.

are only accurate to approx. ± 70%.
* Results of the overall limit of < 50 mg/kg are only accurate to approx. ± 35%