

AAG NR/SBR A605

technical data sheet



10
24/01/2023

General:

SBR, black, commercial
Sulphur crosslinked

Standard quality for minor demands

Wrapping: stretched foil, labelled
standard finishing in talcum

*SVHC-free

Properties:

Hardness [Shore A]:	ISO 48-4	70±7
Density [g/cm³]:	ISO 1183-1	~1,46
Tensile Strength [N/mm²]:	ISO 37 type 2	4
Elongation at Break [%]:	ISO 37 type 2	200

correspond to WDK-guideline 2201 : 2020-10 "Quality characteristics of Elastomer sheets and plates"

Working temperature range

Medium	dyn.(stat.)	max.	short-term
Air	-10 (-30)°C	+70°C	+90°C

Compression set DIN ISO 815

Duration	Temperature	CS
22h	+70°C	50%

Stabilities:

Ozone resistance:	non resistant
Weather resistance:	non resistant
Oil resistance:	non resistant
Fuel resistance:	non resistant
Acid resistance:	moderately resistant
Strong bases:	moderately resistant
Abrasion resistance:	non suitable

ROTACURED SHEETS product number	Thickness mm	Width mm	Length mm
401106100	1,0	1.400	20.000
401106150	1,5	1.400	20.000
401106200	2,0	1.400	20.000
401106300	3,0	1.400	10.000
401106400	4,0	1.400	10.000
401106500	5,0	1.400	10.000
401106600	6,0	1.400	10.000
401106800	8,0	1.400	5.000
401106000	10,0	1.400	5.000

PRESS-CURED SHEETS product number	Thickness mm	Width mm	Length mm
421307120	12,0	1.400	5.000
421307150	15,0	1.400	5.000
421307200	20,0	1.400	5.000
421307250	25,0	1.400	5.000
421307300	30,0	1.400	5.000
421307400	40,0	1.400	5.000
421307500	50,0	1.400	5.000

PAH disclaimer:

Referring to an [international proficiency test](#) and information received from the testing laboratories about accuracy of test results we may inform you, that test results for the same specimen from different laboratories may not correlate:

* Results of the 10 PAH with individual limits of < 1 mg/kg in the measurement range around the limit are only accurate to approx. ± 70%.

* Results of the overall limit of < 50 mg/kg are only accurate to approx. ± 35%

Our test results are provided on an as-is basis and to the best of our knowledge, without any legally binding commitment. Our tests do not release you from own tests as to the respective application envisaged.

*SVHC < 0,1%. Note: for consumer articles with skin contact further restrictions apply according to REACH.

Please note:

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualified engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course warrant the quality of our products according to our General Sales Conditions, available on our website or on request.