

AAG MOOS RUBBER NR

technical data sheet - 15 Shore A



31
26/03/2021

Polymer	NR
Cellstructure	Mixed open and closed cells
Density	0,55 - 0,85 g/cm ³
Hardness Shore A*	15 ± 5°
Elongation in %	250 - 400 %
Compression set according to DIN 53517 at 25 % Deformation 22 h at 23° C	approx. 15 %
Compressibility at 25% Deformation	150 ± 60 kPA
Temperature resistance	+ 70° C
Low temperature flexibility	- 40° C
Flammability	Flammable

*measured on 10 mm Plate; 24 h after vulcanization

Deviations in porosity and surface quality are material-related. We reserve the right to make changes in chemical and technological terms. All information is based on tests carried out. However, it can not be guaranteed that these values coincide with those found in practice. In this connection, specification values are not set.