AAG NITRILE P459

technical data sheet

General:

NBR-SBR, black, high-grade Sulphur crosslinked For medium mechanical demands

Good oil resistant fuel resistant (alcohol-free fuels)

Wrapping: stretched foil, labelled standard finishing in separation foil

*SVHC-free

Working temperature range

vorking temp	erature range		
Medium	dyn.(stat.)	max.	short-term
Air	(-10)°C	+70°C	+90°C
Compression	set DIN ISO 815		
Duration	Temperature		CS
22h	+70°C		40%
geing ISO 18	8		
Conditions	Hardness	Strength	Elongation
70h / 70°C	7 Shore A	10%	20%
welling ISO '	1817		
Medium	Conditions	Hardness	Volume
IRM 903 Fuel B	70h / 100°C 70h / 23°C	10 Shore A	15 % 20 %

ROTACURED SHEETS product number	Thickness mm	Width mm	Length mm
401140100	1,0	1.400	20.000
401140150	1,5	1.400	20.000
401140200	2,0	1.400	20.000
401140300	3,0	1.400	10.000
401140400	4,0	1.400	10.000
401140500	5,0	1.400	10.000
401140600	6,0	1.400	10.000
401140800	8,0	1.400	5.000
401140000	10,0	1.400	5.000

PRESS-CURED SHEETS product number	Thickness mm	Width mm	Length mm
421340120	12,0	1.400	5.000
421340150	15,0	1.400	5.000
421340200	20,0	1.400	5.000
421340250	25,0	1.400	5.000
421340300	30,0	1.400	5.000
421340400	40,0	1.400	5.000
421340500	50,0	1.400	5.000

PAH disclaimer:

Referring to an international proficiency test and information received from the testing laboratories about accuracy of test results we may inform you, that test results for the same specimen from different laboratories may not correlate:

* Results of the 10 PAH with individual limits of < 1 mg/kg in the measurement range around the limit are only accurate to approx. \pm 70%. $^{\circ}$ Results of the overall limit of < 50 mg/kg are only accurate to approx. \pm 35%

Our test results are provided on an as-is basis and to the best of our knowledge, without any legally binding commitment. Our tests do not release you from own tests as to the respective application envisaged.

*SVHC < 0,1%. Note: for consumer articles with skin contact further restrictions apply according to REACH.

Properties:

Hardness [Shore A]:	ISO 48-4	65±5	
Density [g/cm ³]:	ISO 1183-1	~1,45	
Tensile Strength [N/mm ²]:	ISO 37 type 2	7	
Elongation at Break [%]:	ISO 37 type 2	250	
ACN content:		33 %	
correspond to WDK-guideline 2201 : 2020-10 "Quality characteristics			
of Elastomer sheets- and plates"			

^			
Sta	hi	IITI	DC '
ota	NI		U 3.

Ozone resistance: Weather resistance:	non resistant non resistant
Oil resistance:	good resistant
Fuel resistance:	resistant
only alcohol-free fuels!	
Acid resistance:	moderately resistant
Strong bases:	moderately resistant
Abrasion resistance:	non suitable

Please note

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the the result of many years of tests and thats. As individual operation conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualitied engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course warrant the quality of our products according to our General Sales Conditions, available on our website or on request.

AAG | Aalborg Gummivarefabrik A/S | Sundsholmen 3 | DK-9400 Nr. Sundby | Phone +45 98 15 80 22 | info@aag.world | aag.world