AAG RUBBER GRANULATE (CO) technical data sheet

463 19/10 2020

Test methods	Unit	Specification	Typical values
ASTM D1817-05(2016)	kg/m3	1.100-1.200	1.160
EN 1097-3:1998	kg/m3	420 ±8%	420
ISO 13322-2:2006	mm	0,8-3,0	0,8-3,0
DIN 53477:1992-11	%	< 1,0	0,15
ISO 9924-3:2009	%	≥ 40	45
ISO 9924-3:2009	%	< 15	8
ASTM D1509 - 15	%	≤]	≤]
OA-698; (Note 1)	%	≤ 0,004	≤ 0,002
OA-698; (Note 1)	%	≤ 0,002	≤ 0,001
OA-698; (Note 1)	%	≤ 0,1	< 0,04
OA-698; (Note 1)	%	≤ 0,004	≤ 0,002
EN 15051-2:2013		Very low to low	Very low
AfPS GS 2014:01 PAK	mg/kg	≤ 20	< 15
	ASTM D1817-05(2016) EN 1097-3:1998 ISO 13322-2:2006 DIN 53477:1992-11 ISO 9924-3:2009 ISO 9924-3:2009 ASTM D1509 - 15 OA-698; (Note 1) OA-698; (Note 1) OA-698; (Note 1) OA-698; (Note 1) EN 15051-2:2013 AfPS GS 2014:01 PAK	ASTM D1817-05(2016) kg/m3 EN 1097-3:1998 kg/m3 ISO 13322-2:2006 mm DIN 53477:1992-11 % ISO 9924-3:2009 % ISO 9924-3:2009 % ASTM D1509 - 15 % OA-698; (Note 1) % OA-698; (Note 1) % OA-698; (Note 1) % OA-698; (Note 1) % EN 15051-2:2013	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$

Note 1: Non-standardized test method "Determination of bulk density and free impurities in rubber powder and granulate", which your AAG representative will forward upon request. This test method is chosen as values obtained from the use of ASTM 5603 are below the detection limits.

Remarks		
DIN 18035-7:2014-10	AAG rubber granulate complies with all requirements in relation to migration according to DIN 18035-7:2014-10.	
EN 71-3 + A1:2014	AAG rubber granulate complies with all requirements according to EN 71-3 + A1:2014_Safety of Toys - Part 3: Migration of certain elements.	
ASTM F3188-16	AAG rubber granulate complies with all requirements according to ASTM F3188-16_Standard Specification for Extractable Hazardous Metals in Synthetic Turf Infill Materials.	
PAH 8 REACH	A material sample has been extracted in accordance with prEN 17409:2019, and the result is presented as a moving average of the 4 most recent analyses.	
International standards	AAG rubber granulate complies with all requirements for infill according to FIFA 2015, World Rugby 2016 and EN15330-1:2013-12.	
National standards	AAG rubber granulate complies with all requirements for infill according to RAL GZ 944, NF P90-112 and ÖISS.	
Particle size distribution	Information on the actual particle size distribution is available on the relevant sieve curves, which may be downloaded from the AAG website at any time.	
Health & Safety	Guidelines on health and safety are stated in the relevant Safety Data Sheet, which may be downloaded from the AAG website at any time.	

Characteristics stated are typical for the product. The product is derived from a large number of different tyres; consequently, AAG cannot give any exact values on the chemical composition of the material. The above-mentioned characteristics and values have been prepared to the best of our knowledge, and AAG shall not be liable for any insufficiency or inaccuracy in such information.