

AAG PARA A065

datasheet



NR-SBR, natural – high-grade
highly elastic
excellent mechanical properties
packaging see General Information

Hardness [Shore A]: 40 ±5
Density [g/cm³]: 1.06
Tensile strength [N/mm²]: 18
Elongation at break [%]: 600
Ozone resistance: non resistant
Weather resistance: non resistant
Oil resistance: non resistant
Benzine resistance: non resistant
Acid resistance: moderately resistant
Strong bases: resistant
Abrasion resistance: good suitable

WORKING TEMPERATURE RANGE

Medium	dyn. (stat.)	max.	short-term
Air	-40 (-50) °C	+70 °C	+80 °C

COMPRESSION SET DIN ISO 815

Duration	Temperature	CS
22 h	70 °C	25 %

AGING DIN 53508

Conditions	Hardness	Strength	Elongation
70h/70 °C	+3 Shore A	-10 %	-15 %

AUMA-SHEETS

Article-number	Thickness mm	Width m	Length m	Surface	No. of insert.
4101 60050	0.5	1.4	20	S S	0
4011 60100	1.0	1.4	20	S S	0
4011 60150	1.5	1.4	20	S S	0
4011 60200	2.0	1.4	20	S S	0
4011 60300	3.0	1.4	10	S S	0
4011 60400	4.0	1.4	10	S S	0
4011 60500	5.0	1.4	10	S S	0
4011 60600	6.0	1.4	10	S S	0
4011 60800	8.0	1.4	5	S S	0

PRESS-SHEETS

Article-number	Thickness mm	Width m	Length m	Surface	No. of insert.
4213 60100	10.0	1.4	5	S S	0
4213 60120	12.0	1.4	5	S S	0
4213 60150	15.0	1.4	5	S S	0
4213 60200	20.0	1.4	5	S S	0
4213 60250	25.0	1.4	5	S S	0
4213 60300	30.0	1.4	5	S S	0
4213 60400	40.0	1.4	5	S S	0

S = smooth

Please Note:

This catalogue has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this catalogue can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualified engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course guarantee the quality of our products according to our general sales conditions, available on request.